

Technical Data Sheet

Name Scrolljet, no. 904

Structure

Solvent receiver layer
Base paper
Reverse side treatment (lavflat)

Features

- Matt backlit presentation paper
- Ideal for grand format solvent prints
- High colour density for backlit and frontlit situations
- Excellent drying time
- High tear strength in rotating light boxes
- Wet strength base paper
- Homogeneous formation
- High dimensional stability
- Suitable for real solvent and UV curable inks

Specifications

Target values at 23°C / 50% r.H. for general guidance only	Methods	Units	
Substance	DIN ISO 536	g/m ²	175.0
Thickness	DIN 53105 T1	µm	217.0
L* WS	DIN 6174		93.5
a* WS	DIN 6174		1.4
b* WS	DIN 6174		-7.7

The paper should be fed into the inkjet printer according to the printer instructions for use.

The paper should be protected from moisture. Avoid marking the paper with fingerprints.

A relative humidity of over 60% can affect the picture quality.

Printouts with pigmented inks should be protected from smudging for a short time until the pigments have completely anchored themselves in the coating layer.

Edition: August 06

Important: The information given is based on our best knowledge at the time of printing. It is given in good faith and represents neither implied nor actual guarantee and no legal warranty for specific properties or for suitability for a specific application. Responsibility for testing the suitability of the product for specific applications lies with the purchaser. We shall be pleased to aid customers with such tests where possible. Should a claim be taken into consideration, liability will, under no circumstances exceed the value of the goods supplied. Qualimage guarantees the impeccable quality of its goods in accordance with agreed specifications and their standard conditions of sale and delivery.